



GL-5 SAE 85W140

DESCRIPTION:

GL-5 SAE 85W140 Gear Oil is a premium quality multi-purpose gear lubricant which provides superior performance that is obtained through the use of quality base oils and a select extreme pressure additive system. These additives impart anti-weld, anti-scuff and anti-wear properties that are necessary in heavy duty service gear lubricants. **GL-5 SAE 85W140 Gear Oil** provides excellent protection under the most severe conditions encountered in commercial transmissions, axles and final drives. **GL-5 SAE 85W140 Gear Oil** is designed to be used in limited slip differentials.

FEATURES/BENEFITS:

- Excellent product for use in heavy equipment applications which place higher performance demands on the drive train lubricants
- For use in limited slip differentials
- Exceptional reliability in today's drive train applications as well as in the older models
- Provides high thermal stability as well as oxidation resistance
- Protects against low speed/ high torque wear
- Excellent fluidity in low temperatures which reduces wear during start up
- Improved lubrication and extended seal life due to good foam control

APPLICATIONS:

GL-5 SAE 85W140 Gear Oil is recommended for all on-highway heavy and light duty trucks, vans and busses requiring API GL-5 and/or MT-1 type fluids. **GL-5 SAE 85W140 Gear Oil** is also recommended for off-highway applications such as construction, mining, agriculture, and quarrying which require these type fluids. **GL-5 SAE 85W140 Gear Oil** is intended for use in limited slip applications as well.

Meets Performance Requirements:

AGMA 250.04

AGMA 9005-E02

AIST 224

API GL-4

API GL-5

API MT-1

Arvin Meritor axles

Arvin Meritor 0-76-A/B/D/M/N/Q

Cincinnati Milacron

DAF (GL-5 axle lubricants)

David Brown S1.53.101(E)

DIN 51517, Part 3

Eaton

MAN M 3343 Type M

MB 235.0, 235.1, 235.5, 235.6, 235.8

MIL-PRF-2105D

MIL-PRF-2105E

PG-2 Limited Slip

Mercedes Benz 235.20

NATO O-226

Renault (GL-5)

SAE J-2360

Scania: STO 1:0, 2:0A

U.S. Steel 224

Volvo 97310

Volvo 1273.10



Ford WSP-M2C197-A
IVECO (J-2360)
KOMATSU KES 07.861
MACK GO-J
MAN 341 Z-1

ZF TE-ML 02A/B, 05A/B/C4, 07A, 08,
12A/B/C4/E, 16A/B/C/D/E4/F, 17A/B,
19A/B/C, 21A/B
MAN 342 Type M1, M2, M3

* ALWAYS CONSULT YOUR OWNER'S MANUAL FOR THE PROPER FLUID FOR YOUR EQUIPMENT.

TYPICAL TEST DATA

SAE GRADE	85W140
Specific Gravity @ 60 °F	0.8925
Viscosity, Kinematic cSt at 40°C cSt at 100°C	367.2 27.44
Viscosity Index	101
Viscosity, Brookfield cP at -12°C Max	150,000
Flash Point, °F	415
Pour Point, °C (°F)	-15 (5)
Color	4.0

Typical test data are average values only. Minor variations which do not affect product performance are to be expected during normal manufacturing.